

## APPLICANT

**F.I.L.A. - FABBRICA ITALIANA LAPIS ED AFFINI SPA**  
**Via Meucci, 2**  
**50068 Rufina FI**

SAMPLE  
DESCRIPTION

Quotation No. 2134DB  
 Receiving Date: 12/07/2021  
 Quantity: 24 pieces  
 Name: Pastelli a cera Giotto Cera e Giotto Cera Maxi  
 Batch No.: Giotto Cera Bianco/White - lotto T12M;  
 Giotto Cera Giallo Limone/LemonYellow - lotto T04M;  
 Giotto Cera Giallo/Yellow - lotto T11M;  
 Giotto Cera Ocra Giallo/Yellow Ochre - lotto T06M;  
 Giotto Cera Vere Scuro/Dark Green - lotto T12M;  
 Giotto Cera Acquamarina/Turquoise - lotto T12M;  
 Giotto Cera Verde Smeraldo/Emerald Green - lotto T12M;  
 Giotto Cera Verde Chiaro/Light Green - lotto T11M;  
 Giotto Cera Rosa Carne/Flesh Pink - lotto T10M;  
 Giotto Cera Rosa/Pink - lotto T12M;  
 Giotto Cera Arancio/Orange - lotto T12M;  
 Giotto Cera Magenta/Magenta - lotto T09M;  
 Giotto Cera Rosso Scarlatto/Scarlet Red - lotto T12M;  
 Giotto Cera Rosso Carminio/Carmin Red - lotto T04M;  
 Giotto Cera Marrone/Brown - lotto T12M;  
 Giotto Cera Terra di Siena Naturale/Natural Sienna - lotto T05M;  
 Giotto Cera Celeste/Sky Blue - lotto T12M;  
 Giotto Cera Blu Cobalto/Cobalt Blue - lotto T12M;  
 Giotto Cera Blu Oltremare/Ultramarine Blue - lotto T12M;  
 Giotto Cera Blu Avio/Navy Blue - lotto T09M;  
 Giotto Cera Porpora/Purple - lotto T05M;  
 Giotto Cera Viola/Violet - lotto T12M;  
 Giotto Cera Grigio/Grey - lotto T10M;  
 Giotto Cera Nero/Black - lotto T12M.

Labelled Age: 2+  
 Sample Return No  
 Buyer's Name: F.I.L.A. - FABBRICA ITALIANA LAPIS ED AFFINI SPA

## Sample 01 SAMPLE DESCRIPTION: WHITE WAX (GIOTTO CERA BIANCO/WHITE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 02 SAMPLE DESCRIPTION: YELLOW WAX (GIOTTO CERA GIALLO LIMONE/LEMONYELLOW).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |



LAB N° 0579 L

## Sample 03 SAMPLE DESCRIPTION: YELLOW WAX (GIOTTO CERA GIALLO/YELLOW).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 04 SAMPLE DESCRIPTION: DEEP YELLOW WAX (GIOTTO CERA OCRA GIALLO/YELLOW OCHRE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 05 SAMPLE DESCRIPTION: DEEP GREEN WAX (GIOTTO CERA VERE SCURO/DARK GREEN).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 06 SAMPLE DESCRIPTION: GREEN WAX (GIOTTO CERA ACQUAMARINA/TURQUOISE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 07 SAMPLE DESCRIPTION: GREEN WAX (GIOTTO CERA VERDE SMERALDO/EMERALD GREEN).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 08 SAMPLE DESCRIPTION: LIGHT GREEN WAX (GIOTTO CERA VERDE CHIARO/LIGHT GREEN).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 09 SAMPLE DESCRIPTION: LIGHT PINK WAX (GIOTTO CERA ROSA CARNE/FLESH PINK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 10 SAMPLE DESCRIPTION: PINK WAX (GIOTTO CERA ROSA/PINK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 11 SAMPLE DESCRIPTION: ORANGE WAX (GIOTTO CERA ARANCIO/ORANGE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 12 SAMPLE DESCRIPTION: MAGENTA WAX (GIOTTO CERA MAGENTA/MAGENTA).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 13 SAMPLE DESCRIPTION: RED WAX (GIOTTO CERA ROSSO SCARLATTO/SCARLET RED).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 14 SAMPLE DESCRIPTION: RED WAX (GIOTTO CERA ROSSO CARMINIO/CARMINE RED).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 15 SAMPLE DESCRIPTION: BROWN WAX (GIOTTO CERA MARRONE/BROWN).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 16 SAMPLE DESCRIPTION: BROWN WAX (GIOTTO CERA TERRA DI SIENA NATURALE/NATURAL SIENNA).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |



LAB N° 0579 L

## Sample 17 SAMPLE DESCRIPTION: LIGHT BLUE WAX (GIOTTO CERA CELESTE/SKY BLUE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 18 SAMPLE DESCRIPTION: DEEP BLUE WAX (GIOTTO CERA BLU COBALTO/COBALT BLUE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 19 SAMPLE DESCRIPTION: DEEP BLUE WAX (GIOTTO CERA BLU OLTREMARE/ULTRAMARINE BLUE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 20 SAMPLE DESCRIPTION: DEEP BLUE WAX (GIOTTO CERA BLU AVIO/NAVY BLUE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 21 SAMPLE DESCRIPTION: PURPLE WAX (GIOTTO CERA PORPORA/PURPLE).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 22 SAMPLE DESCRIPTION: VIOLET WAX (GIOTTO CERA VIOLA/VIOLET).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 23 SAMPLE DESCRIPTION: GREY WAX (GIOTTO CERA GRIGIO/GREY).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 24 SAMPLE DESCRIPTION: BLACK WAX (GIOTTO CERA NERO/BLACK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 25 SAMPLE DESCRIPTION: WHITE PAPER WITH SKY BLUE PRINTING (CYAN INK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 26 SAMPLE DESCRIPTION: WHITE PAPER WITH RED PRINTING (RED INK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 27 SAMPLE DESCRIPTION: WHITE PAPER WITH YELLOW PRINTING (YELLOW INK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

## Sample 28 SAMPLE DESCRIPTION: WHITE PAPER WITH GREY PRINTING (BLACK INK).

| Test                                                                       | Rating | Failure result |
|----------------------------------------------------------------------------|--------|----------------|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | P      |                |

P = MEETS REQUIREMENT / A = ACCEPTABLE / F = DOES NOT MEET REQUIREMENT / NR = NO REQUIREMENT / SC = STILL CONTINUES / X = NOT PERFORMED  
Values in brackets represent the limits



LAB N° 0579 L

| TEST METHOD                                                                | SAMPLE DESCRIPTION                                                                   | PARAMETERS   | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|----------------------------------------------------------------------------|--------------------------------------------------------------------------------------|--------------|--------|-------|--------|------|-----------|-----|
| Specification for Migration of Certain Elements<br>EN 71-3: 2019 + A1:2021 | 01<br>SAMPLE DESCRIPTION:<br>WHITE WAX<br>(GIOTTO CERA BIANCO/WHITE).                | Alluminium   | 43     | mg/kg | 2250   | 5    |           | ITA |
|                                                                            |                                                                                      | 7429-90-5    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Antimony     | < 1    | mg/kg | 45     | 1    |           | ITA |
|                                                                            |                                                                                      | 7440-36-0    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Arsenic      | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|                                                                            |                                                                                      | 7440-38-2    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Barium       | 341    | mg/kg | 1500   | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-39-3    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Boron        | < 5    | mg/kg | 1200   | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-42-8    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Cadmium      | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|                                                                            |                                                                                      | 7440-43-9    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Chromium III | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|                                                                            |                                                                                      | 16065-83-1   |        |       |        |      |           |     |
|                                                                            |                                                                                      | Chromium VI  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|                                                                            |                                                                                      | 18540-29-9   |        |       |        |      |           |     |
|                                                                            |                                                                                      | Cobalt       | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|                                                                            |                                                                                      | 7440-48-4    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Copper       | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-50-8    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Lead         | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|                                                                            |                                                                                      | 7439-92-1    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Manganese    | 15     | mg/kg | 1200   | 5    |           | ITA |
|                                                                            |                                                                                      | 7439-96-5    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Mercury      | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|                                                                            |                                                                                      | 7439-97-6    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Nickel       | < 5    | mg/kg | 75     | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-02-0    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Selenium     | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|                                                                            |                                                                                      | 7782-49-2    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Strontium    | 32     | mg/kg | 4500   | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-24-6    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Tin          | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|                                                                            |                                                                                      | 7440-31-5    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Zinc         | 424    | mg/kg | 3750   | 5    |           | ITA |
|                                                                            |                                                                                      | 7440-66-6    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Organic Tin  | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|                                                                            | 02<br>SAMPLE DESCRIPTION:<br>YELLOW WAX<br>(GIOTTO CERA GIALLO LIMONE/LEMONYEL LOW). | Alluminium   | 73     | mg/kg | 2250   | 5    |           | ITA |
|                                                                            |                                                                                      | 7429-90-5    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Antimony     | < 1    | mg/kg | 45     | 1    |           | ITA |
|                                                                            |                                                                                      | 7440-36-0    |        |       |        |      |           |     |
|                                                                            |                                                                                      | Arsenic      | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|                                                                            |                                                                                      | 7440-38-2    |        |       |        |      |           |     |



LAB N° 0579 L

Laboratory Manager


*Ilaria Francioni*  
Ilaria Francioni  
ilenia.francioni@intertek.com

| TEST METHOD | SAMPLE DESCRIPTION                                                            | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                               | Barium<br>7440-39-3        | 8      | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                               | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                               | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                               | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                               | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                               | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                               | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                               | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                               | Manganese<br>7439-96-5     | 16     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                               | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                               | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                               | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                               | Strontium<br>7440-24-6     | 6      | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                               | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                               | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                               | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 03<br>SAMPLE<br>DESCRIPTION:<br>YELLOW WAX<br>(GIOTTO CERA<br>GIALLO/YELLOW). | Alluminium<br>7429-90-5    | 34     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                               | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                               | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                               | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                               | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                               | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                               | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                               | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                               | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                                  | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-----------------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                                     | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                     | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                     | Manganese<br>7439-96-5     | 11     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                     | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                                     | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                     | Strontium<br>7440-24-6     | 17     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                                     | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                                     | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                     | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 04<br>SAMPLE<br>DESCRIPTION: DEEP<br>YELLOW WAX<br>(GIOTTO CERA<br>OCRA<br>GIALLO/YELLOW<br>OCHRE). | Alluminium<br>7429-90-5    | 64     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                                     | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                                     | Arsenic<br>7440-38-2       | 0,2    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                     | Barium<br>7440-39-3        | 14     | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                     | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                     | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                     | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                     | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                     | Copper<br>7440-50-8        | 6      | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                     | Lead<br>7439-92-1          | 0,3    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                     | Manganese<br>7439-96-5     | 17     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                     | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)


| TEST METHOD | SAMPLE DESCRIPTION                                                                           | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|----------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                              | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                              | Strontium<br>7440-24-6     | 24     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                              | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                              | Zinc<br>7440-66-6          | 6      | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                              | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 05<br>SAMPLE<br>DESCRIPTION: DEEP<br>GREEN WAX<br>(GIOTTO CERA<br>VERE SCURO/DARK<br>GREEN). | Alluminium<br>7429-90-5    | 47     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                              | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                              | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                              | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                              | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                              | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                              | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                              | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                              | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                              | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                              | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                              | Manganese<br>7439-96-5     | 11     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                              | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                              | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                              | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                              | Strontium<br>7440-24-6     | 17     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                              | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                              | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                              | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)



Ilenia Francioni  
ilenia.francioni@intertek.com

Validated by: Giovanni Servadei



| TEST METHOD | SAMPLE DESCRIPTION                                                                                  | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-----------------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                                     | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                     | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                     | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                     | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                     | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                     | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                     | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                     | Lead<br>7439-92-1          | 0,2    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                     | Manganese<br>7439-96-5     | 11     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                     | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                                     | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                     | Strontium<br>7440-24-6     | 18     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                                     | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                                     | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                     | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 08<br>SAMPLE<br>DESCRIPTION:<br>LIGHT GREEN WAX<br>(GIOTTO CERA<br>VERDE<br>CHIARO/LIGHT<br>GREEN). | Alluminium<br>7429-90-5    | 81     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                                     | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                                     | Arsenic<br>7440-38-2       | 0,3    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                     | Barium<br>7440-39-3        | 8      | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                     | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                     | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                     | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |



LAB N° 0579 L

Laboratory Manager


*Ilaria Francioni*  
 Ilaria Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                              | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-------------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                                 | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                 | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                 | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                 | Lead<br>7439-92-1          | 0,4    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                 | Manganese<br>7439-96-5     | 19     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                 | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                 | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                                 | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                 | Strontium<br>7440-24-6     | 31     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                                 | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                                 | Zinc<br>7440-66-6          | 6      | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                 | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 09<br>SAMPLE<br>DESCRIPTION:<br>LIGHT PINK WAX<br>(GIOTTO CERA<br>ROSA<br>CARNE/FLESH<br>PINK). | Alluminium<br>7429-90-5    | 63     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                                 | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                                 | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                 | Barium<br>7440-39-3        | 143    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                 | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                 | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                 | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                 | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                 | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                 | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                 | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                 | Manganese<br>7439-96-5     | 15     | mg/kg | 1200   | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                   | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|----------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                      | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                      | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                      | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                      | Strontium<br>7440-24-6     | 25     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                      | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                      | Zinc<br>7440-66-6          | 46     | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                      | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 10<br>SAMPLE<br>DESCRIPTION: PINK<br>WAX (GIOTTO CERA<br>ROSA/PINK). | Alluminium<br>7429-90-5    | 66     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                      | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                      | Arsenic<br>7440-38-2       | 0,3    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                      | Barium<br>7440-39-3        | 5      | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                      | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                      | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                      | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                      | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                      | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                      | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                      | Lead<br>7439-92-1          | 0,2    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                      | Manganese<br>7439-96-5     | 19     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                      | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                      | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                      | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                      | Strontium<br>7440-24-6     | 29     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                      | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                      | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                             | PARAMETERS                 | RESULT                                                                               | U.M.                    | LIMITS | LQ    | NOTES     | LAB |  |     |
|-------------|--------------------------------------------------------------------------------|----------------------------|--------------------------------------------------------------------------------------|-------------------------|--------|-------|-----------|-----|--|-----|
|             |                                                                                | Organic Tin                | < 0,5                                                                                | mg/kg                   | 0,9    | 0,5   | #tin<br>* | ITA |  |     |
|             | 11<br>SAMPLE<br>DESCRIPTION:<br>ORANGE WAX<br>(GIOTTO CERA<br>ARANCIO/ORANGE). | Alluminium<br>7429-90-5    | 86                                                                                   | mg/kg                   | 2250   | 5     | *         | ITA |  |     |
|             |                                                                                | Antimony<br>7440-36-0      | < 1                                                                                  | mg/kg                   | 45     | 1     |           | ITA |  |     |
|             |                                                                                | Arsenic<br>7440-38-2       | < 0,2                                                                                | mg/kg                   | 3,8    | 0,2   |           | ITA |  |     |
|             |                                                                                | Barium<br>7440-39-3        | < 5                                                                                  | mg/kg                   | 1500   | 5     |           | ITA |  |     |
|             |                                                                                | Boron<br>7440-42-8         | < 5                                                                                  | mg/kg                   | 1200   | 5     |           | ITA |  |     |
|             |                                                                                | Cadmium<br>7440-43-9       | < 0,1                                                                                | mg/kg                   | 1,3    | 0,1   |           | ITA |  |     |
|             |                                                                                | Chromium III<br>16065-83-1 | < 1                                                                                  | mg/kg                   | 37,5   | 1     |           | ITA |  |     |
|             |                                                                                | Chromium VI<br>18540-29-9  | < 0,02                                                                               | mg/kg                   | 0,02   | 0,02  |           | ITA |  |     |
|             |                                                                                | Cobalt<br>7440-48-4        | < 1                                                                                  | mg/kg                   | 10,5   | 1     |           | ITA |  |     |
|             |                                                                                | Copper<br>7440-50-8        | < 5                                                                                  | mg/kg                   | 622,5  | 5     |           | ITA |  |     |
|             |                                                                                | Lead<br>7439-92-1          | < 0,2                                                                                | mg/kg                   | 2,0    | 0,2   |           | ITA |  |     |
|             |                                                                                | Manganese<br>7439-96-5     | 15                                                                                   | mg/kg                   | 1200   | 5     |           | ITA |  |     |
|             |                                                                                | Mercury<br>7439-97-6       | < 0,5                                                                                | mg/kg                   | 7,5    | 0,5   |           | ITA |  |     |
|             |                                                                                | Nickel<br>7440-02-0        | < 5                                                                                  | mg/kg                   | 75     | 5     |           | ITA |  |     |
|             |                                                                                | Selenium<br>7782-49-2      | < 1                                                                                  | mg/kg                   | 37,5   | 1     |           | ITA |  |     |
|             |                                                                                | Strontium<br>7440-24-6     | 5                                                                                    | mg/kg                   | 4500   | 5     |           | ITA |  |     |
|             |                                                                                | Tin<br>7440-31-5           | < 0,2                                                                                | mg/kg                   | 15000  | 0,2   |           | ITA |  |     |
|             |                                                                                | Zinc<br>7440-66-6          | < 5                                                                                  | mg/kg                   | 3750   | 5     |           | ITA |  |     |
|             |                                                                                | Organic Tin                | < 0,5                                                                                | mg/kg                   | 0,9    | 0,5   | #tin<br>* | ITA |  |     |
|             |                                                                                |                            | 12<br>SAMPLE<br>DESCRIPTION:<br>MAGENTA WAX<br>(GIOTTO CERA<br>MAGENTA/MAGEN<br>TA). | Alluminium<br>7429-90-5 | 54     | mg/kg | 2250      | 5   |  | ITA |
|             |                                                                                |                            |                                                                                      | Antimony<br>7440-36-0   | < 1    | mg/kg | 45        | 1   |  | ITA |
|             |                                                                                |                            |                                                                                      |                         |        |       |           |     |  |     |



LAB N° 0579 L

Laboratory Manager

Ilenia Francioni  
ilenia.francioni@intertek.com

Validated by: Giovanni Servadei

**Intertek Italia S.p.a.**  
**Administrative Office** Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)  
**Operational Office** Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)  
**Tel. 0039055790873 Fax 0039055791198**


page 12 di 27

| TEST METHOD | SAMPLE DESCRIPTION                                                                           | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|----------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                              | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                              | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                              | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                              | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                              | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                              | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                              | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                              | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                              | Lead<br>7439-92-1          | 0,2    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                              | Manganese<br>7439-96-5     | 11     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                              | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                              | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                              | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                              | Strontium<br>7440-24-6     | 16     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                              | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                              | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                              | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 13<br>SAMPLE<br>DESCRIPTION: RED<br>WAX (GIOTTO CERA<br>ROSSO<br>SCARLATTO/SCARLE<br>T RED). | Alluminium<br>7429-90-5    | 43     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                              | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                              | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                              | Barium<br>7440-39-3        | 11     | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                              | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                              | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                              | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                          | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|---------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                             | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                             | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                             | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                             | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                             | Manganese<br>7439-96-5     | 12     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                             | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                             | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                             | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                             | Strontium<br>7440-24-6     | 19     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                             | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                             | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                             | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 14<br>SAMPLE<br>DESCRIPTION: RED<br>WAX (GIOTTO CERA<br>ROSSO<br>CARMINIO/CARMIN<br>E RED). | Alluminium<br>7429-90-5    | 82     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                             | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                             | Arsenic<br>7440-38-2       | 0,2    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                             | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                             | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                             | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                             | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                             | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                             | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                             | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                             | Lead<br>7439-92-1          | 0,2    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                             | Manganese<br>7439-96-5     | 16     | mg/kg | 1200   | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


*Il*  
Ilenia Francioni  
ilenia.francioni@intertek.com

| TEST METHOD | SAMPLE DESCRIPTION                                                          | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-----------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                             | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                             | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                             | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                             | Strontium<br>7440-24-6     | 22     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                             | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                             | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                             | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 15<br>SAMPLE<br>DESCRIPTION:<br>BROWN WAX<br>(GIOTTO CERA<br>MARRONE/BROWN) | Alluminium<br>7429-90-5    | 32     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                             | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                             | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                             | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                             | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                             | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                             | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                             | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                             | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                             | Copper<br>7440-50-8        | 6      | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                             | Lead<br>7439-92-1          | 0,2    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                             | Manganese<br>7439-96-5     | 10     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                             | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                             | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                             | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                             | Strontium<br>7440-24-6     | 15     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                             | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                                           | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|--------------------------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                                              | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                              | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 16<br>SAMPLE<br>DESCRIPTION:<br>BROWN WAX<br>(GIOTTO CERA<br>TERRA DI SIENA<br>NATURALE/NATURA<br>L SIENNA). | Alluminium<br>7429-90-5    | 48     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                                              | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                                              | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                              | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                              | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                              | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                              | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                              | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                              | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                              | Copper<br>7440-50-8        | 5      | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                              | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                              | Manganese<br>7439-96-5     | 13     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                              | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                              | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                                              | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                              | Strontium<br>7440-24-6     | < 5    | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                                              | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                                              | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                              | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)



**Intertek Italia S.p.a.**

**Administrative Office Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)**  
**Operational Office Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)**  
**Tel. 0039055790873 Fax 0039055791198**

Ilenia Francioni

ilenia.francioni@intertek.com


Validated by: Giovanni Servadei

| TEST METHOD | SAMPLE DESCRIPTION                                                                                    | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|-------------------------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                                       | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                       | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                       | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                       | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                       | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                                       | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                                       | Copper<br>7440-50-8        | 6      | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                                       | Lead<br>7439-92-1          | 0,3    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                                       | Manganese<br>7439-96-5     | 14     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                       | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                                       | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                                       | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                       | Strontium<br>7440-24-6     | 22     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                                       | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                                       | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                                       | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 19<br>SAMPLE<br>DESCRIPTION: DEEP<br>BLUE WAX (GIOTTO<br>CERA BLU<br>OLTREMARE/ULTRA<br>MARINE BLUE). | Alluminium<br>7429-90-5    | 79     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                                       | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                                       | Arsenic<br>7440-38-2       | 0,3    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                                       | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                                       | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                                       | Cadmium<br>7440-43-9       | 0,1    | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                                       | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                                       | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                    | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|---------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                       | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                       | Copper<br>7440-50-8        | 7      | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                       | Lead<br>7439-92-1          | 0,3    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                       | Manganese<br>7439-96-5     | 21     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                       | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                       | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                       | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                       | Strontium<br>7440-24-6     | 31     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                       | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                       | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                       | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 20<br>SAMPLE<br>DESCRIPTION: DEEP<br>BLUE WAX (GIOTTO<br>CERA BLU<br>AVIO/NAVY BLUE). | Alluminium<br>7429-90-5    | 85     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                       | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                       | Arsenic<br>7440-38-2       | 0,2    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                       | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                       | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                       | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                       | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                       | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                       | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                       | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                       | Lead<br>7439-92-1          | 0,3    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                       | Manganese<br>7439-96-5     | 13     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                       | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                       | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                             | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|--------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                | Strontium<br>7440-24-6     | 21     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 21<br>SAMPLE<br>DESCRIPTION:<br>PURPLE WAX<br>(GIOTTO CERA<br>PORPORA/PURPLE). | Alluminium<br>7429-90-5    | 89     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                                | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                                | Arsenic<br>7440-38-2       | < 0,2  | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                                | Barium<br>7440-39-3        | 16     | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                                | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                                | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                                | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                                | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                                | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                | Manganese<br>7439-96-5     | 21     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                | Strontium<br>7440-24-6     | 8      | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                     | PARAMETERS                 | RESULT                                                              | U.M.                   | LIMITS | LQ    | NOTES     | LAB |  |     |
|-------------|------------------------------------------------------------------------|----------------------------|---------------------------------------------------------------------|------------------------|--------|-------|-----------|-----|--|-----|
|             | 22<br>SAMPLE DESCRIPTION:<br>VIOLET WAX<br>(GIOTTO CERA VIOLA/VIOLET). | Aluminium<br>7429-90-5     | 83                                                                  | mg/kg                  | 2250   | 5     |           | ITA |  |     |
|             |                                                                        | Antimony<br>7440-36-0      | < 1                                                                 | mg/kg                  | 45     | 1     |           | ITA |  |     |
|             |                                                                        | Arsenic<br>7440-38-2       | 0,3                                                                 | mg/kg                  | 3,8    | 0,2   |           | ITA |  |     |
|             |                                                                        | Barium<br>7440-39-3        | < 5                                                                 | mg/kg                  | 1500   | 5     |           | ITA |  |     |
|             |                                                                        | Boron<br>7440-42-8         | < 5                                                                 | mg/kg                  | 1200   | 5     |           | ITA |  |     |
|             |                                                                        | Cadmium<br>7440-43-9       | < 0,1                                                               | mg/kg                  | 1,3    | 0,1   |           | ITA |  |     |
|             |                                                                        | Chromium III<br>16065-83-1 | < 1                                                                 | mg/kg                  | 37,5   | 1     |           | ITA |  |     |
|             |                                                                        | Chromium VI<br>18540-29-9  | < 0,02                                                              | mg/kg                  | 0,02   | 0,02  | *         | ITA |  |     |
|             |                                                                        | Cobalt<br>7440-48-4        | < 1                                                                 | mg/kg                  | 10,5   | 1     |           | ITA |  |     |
|             |                                                                        | Copper<br>7440-50-8        | < 5                                                                 | mg/kg                  | 622,5  | 5     |           | ITA |  |     |
|             |                                                                        | Lead<br>7439-92-1          | 0,4                                                                 | mg/kg                  | 2,0    | 0,2   |           | ITA |  |     |
|             |                                                                        | Manganese<br>7439-96-5     | 18                                                                  | mg/kg                  | 1200   | 5     |           | ITA |  |     |
|             |                                                                        | Mercury<br>7439-97-6       | < 0,5                                                               | mg/kg                  | 7,5    | 0,5   |           | ITA |  |     |
|             |                                                                        | Nickel<br>7440-02-0        | < 5                                                                 | mg/kg                  | 75     | 5     |           | ITA |  |     |
|             |                                                                        | Selenium<br>7782-49-2      | < 1                                                                 | mg/kg                  | 37,5   | 1     |           | ITA |  |     |
|             |                                                                        | Strontium<br>7440-24-6     | 31                                                                  | mg/kg                  | 4500   | 5     |           | ITA |  |     |
|             |                                                                        | Tin<br>7440-31-5           | < 0,2                                                               | mg/kg                  | 15000  | 0,2   |           | ITA |  |     |
|             |                                                                        | Zinc<br>7440-66-6          | < 5                                                                 | mg/kg                  | 3750   | 5     |           | ITA |  |     |
|             |                                                                        | Organic Tin                | < 0,5                                                               | mg/kg                  | 0,9    | 0,5   | #tin<br>* | ITA |  |     |
|             |                                                                        |                            | 23<br>SAMPLE DESCRIPTION:<br>GREY WAX<br>(GIOTTO CERA GRIGIO/GREY). | Aluminium<br>7429-90-5 | 83     | mg/kg | 2250      | 5   |  | ITA |
|             |                                                                        |                            |                                                                     | Antimony<br>7440-36-0  | < 1    | mg/kg | 45        | 1   |  | ITA |
|             |                                                                        |                            |                                                                     | Arsenic<br>7440-38-2   | < 0,2  | mg/kg | 3,8       | 0,2 |  | ITA |
|             |                                                                        |                            |                                                                     | Barium<br>7440-39-3    | < 5    | mg/kg | 1500      | 5   |  | ITA |



**Intertek Italia S.p.a.**  
**Administrative Office Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)**  
**Operational Office Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)**  
**Tel. 0039055790873 Fax 0039055791198**

Ilenia Francioni  
ilenia.francioni@intertek.com

Validated by: Giovanni Servadei

| TEST METHOD | SAMPLE DESCRIPTION                                                        | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|---------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                           | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                           | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                           | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                           | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                           | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                           | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |
|             |                                                                           | Lead<br>7439-92-1          | < 0,2  | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                           | Manganese<br>7439-96-5     | 20     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                           | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                           | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                           | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                           | Strontium<br>7440-24-6     | 7      | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                           | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                           | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                           | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 24<br>SAMPLE<br>DESCRIPTION:<br>BLACK WAX<br>(GIOTTO CERA<br>NERO/BLACK). | Alluminium<br>7429-90-5    | 72     | mg/kg | 2250   | 5    |           | ITA |
|             |                                                                           | Antimony<br>7440-36-0      | < 1    | mg/kg | 45     | 1    |           | ITA |
|             |                                                                           | Arsenic<br>7440-38-2       | 0,2    | mg/kg | 3,8    | 0,2  |           | ITA |
|             |                                                                           | Barium<br>7440-39-3        | < 5    | mg/kg | 1500   | 5    |           | ITA |
|             |                                                                           | Boron<br>7440-42-8         | < 5    | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                           | Cadmium<br>7440-43-9       | < 0,1  | mg/kg | 1,3    | 0,1  |           | ITA |
|             |                                                                           | Chromium III<br>16065-83-1 | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                           | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,02   | 0,02 | *         | ITA |
|             |                                                                           | Cobalt<br>7440-48-4        | < 1    | mg/kg | 10,5   | 1    |           | ITA |
|             |                                                                           | Copper<br>7440-50-8        | < 5    | mg/kg | 622,5  | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


*Ilaria Francioni*  
 Ilaria Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                                   | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|--------------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                      | Lead<br>7439-92-1          | 0,4    | mg/kg | 2,0    | 0,2  |           | ITA |
|             |                                                                                      | Manganese<br>7439-96-5     | 19     | mg/kg | 1200   | 5    |           | ITA |
|             |                                                                                      | Mercury<br>7439-97-6       | < 0,5  | mg/kg | 7,5    | 0,5  |           | ITA |
|             |                                                                                      | Nickel<br>7440-02-0        | < 5    | mg/kg | 75     | 5    |           | ITA |
|             |                                                                                      | Selenium<br>7782-49-2      | < 1    | mg/kg | 37,5   | 1    |           | ITA |
|             |                                                                                      | Strontium<br>7440-24-6     | 27     | mg/kg | 4500   | 5    |           | ITA |
|             |                                                                                      | Tin<br>7440-31-5           | < 0,2  | mg/kg | 15000  | 0,2  |           | ITA |
|             |                                                                                      | Zinc<br>7440-66-6          | < 5    | mg/kg | 3750   | 5    |           | ITA |
|             |                                                                                      | Organic Tin                | < 0,5  | mg/kg | 0,9    | 0,5  | #tin<br>* | ITA |
|             | 25<br>SAMPLE<br>DESCRIPTION:<br>WHITE PAPER WITH<br>SKY BLUE PRINTING<br>(CYAN INK). | Alluminium<br>7429-90-5    | 10     | mg/kg | 28130  | 5    |           | ITA |
|             |                                                                                      | Antimony<br>7440-36-0      | < 5    | mg/kg | 560    | 5    |           | ITA |
|             |                                                                                      | Arsenic<br>7440-38-2       | < 5    | mg/kg | 47     | 5    |           | ITA |
|             |                                                                                      | Barium<br>7440-39-3        | 30     | mg/kg | 18750  | 5    |           | ITA |
|             |                                                                                      | Boron<br>7440-42-8         | < 5    | mg/kg | 15000  | 5    |           | ITA |
|             |                                                                                      | Cadmium<br>7440-43-9       | < 1    | mg/kg | 17     | 1    |           | ITA |
|             |                                                                                      | Chromium III<br>16065-83-1 | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                                                                                      | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,053  | 0,02 | *         | ITA |
|             |                                                                                      | Cobalt<br>7440-48-4        | < 5    | mg/kg | 130    | 5    |           | ITA |
|             |                                                                                      | Copper<br>7440-50-8        | < 5    | mg/kg | 7700   | 5    |           | ITA |
|             |                                                                                      | Lead<br>7439-92-1          | < 5    | mg/kg | 23     | 5    |           | ITA |
|             |                                                                                      | Manganese<br>7439-96-5     | 15     | mg/kg | 15000  | 5    |           | ITA |
|             |                                                                                      | Mercury<br>7439-97-6       | < 5    | mg/kg | 94     | 5    |           | ITA |
|             |                                                                                      | Nickel<br>7440-02-0        | < 5    | mg/kg | 930    | 5    |           | ITA |
|             |                                                                                      | Selenium<br>7782-49-2      | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                                                                                      | Strontium<br>7440-24-6     | 59     | mg/kg | 56000  | 5    |           | ITA |



LAB N° 0579 L

Laboratory Manager


  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

| TEST METHOD | SAMPLE DESCRIPTION                                                             | PARAMETERS                 | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|--------------------------------------------------------------------------------|----------------------------|--------|-------|--------|------|-----------|-----|
|             |                                                                                | Tin<br>7440-31-5           | < 3,25 | mg/kg | 180000 | 3,25 |           | ITA |
|             |                                                                                | Zinc<br>7440-66-6          | < 5    | mg/kg | 46000  | 5    |           | ITA |
|             |                                                                                | Organic Tin                | < 8    | mg/kg | 12     | 8    | #tin<br>* | ITA |
|             | 26<br>SAMPLE<br>DESCRIPTION:<br>WHITE PAPER WITH<br>RED PRINTING (RED<br>INK). | Alluminium<br>7429-90-5    | 7      | mg/kg | 28130  | 5    |           | ITA |
|             |                                                                                | Antimony<br>7440-36-0      | < 5    | mg/kg | 560    | 5    |           | ITA |
|             |                                                                                | Arsenic<br>7440-38-2       | < 5    | mg/kg | 47     | 5    |           | ITA |
|             |                                                                                | Barium<br>7440-39-3        | < 5    | mg/kg | 18750  | 5    |           | ITA |
|             |                                                                                | Boron<br>7440-42-8         | < 5    | mg/kg | 15000  | 5    |           | ITA |
|             |                                                                                | Cadmium<br>7440-43-9       | < 1    | mg/kg | 17     | 1    |           | ITA |
|             |                                                                                | Chromium III<br>16065-83-1 | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                                                                                | Chromium VI<br>18540-29-9  | < 0,02 | mg/kg | 0,053  | 0,02 | *         | ITA |
|             |                                                                                | Cobalt<br>7440-48-4        | 10     | mg/kg | 130    | 5    |           | ITA |
|             |                                                                                | Copper<br>7440-50-8        | < 5    | mg/kg | 7700   | 5    |           | ITA |
|             |                                                                                | Lead<br>7439-92-1          | < 5    | mg/kg | 23     | 5    |           | ITA |
|             |                                                                                | Manganese<br>7439-96-5     | 20     | mg/kg | 15000  | 5    |           | ITA |
|             |                                                                                | Mercury<br>7439-97-6       | < 5    | mg/kg | 94     | 5    |           | ITA |
|             |                                                                                | Nickel<br>7440-02-0        | < 5    | mg/kg | 930    | 5    |           | ITA |
|             |                                                                                | Selenium<br>7782-49-2      | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                                                                                | Strontium<br>7440-24-6     | 36     | mg/kg | 56000  | 5    |           | ITA |
|             |                                                                                | Tin<br>7440-31-5           | < 3,25 | mg/kg | 180000 | 3,25 |           | ITA |
|             |                                                                                | Zinc<br>7440-66-6          | < 5    | mg/kg | 46000  | 5    |           | ITA |
|             |                                                                                | Organic Tin                | < 8    | mg/kg | 12     | 8    | #tin<br>* | ITA |



LAB N° 0579 L

Laboratory Manager

  
 Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)



| TEST METHOD | SAMPLE DESCRIPTION                                                                | PARAMETERS                 | RESULT                                                                         | U.M.                   | LIMITS | LQ    | NOTES     | LAB |  |     |
|-------------|-----------------------------------------------------------------------------------|----------------------------|--------------------------------------------------------------------------------|------------------------|--------|-------|-----------|-----|--|-----|
|             | 27<br>SAMPLE DESCRIPTION:<br>WHITE PAPER WITH<br>YELLOW PRINTING<br>(YELLOW INK). | Aluminium<br>7429-90-5     | 11                                                                             | mg/kg                  | 28130  | 5     |           | ITA |  |     |
|             |                                                                                   | Antimony<br>7440-36-0      | < 5                                                                            | mg/kg                  | 560    | 5     |           | ITA |  |     |
|             |                                                                                   | Arsenic<br>7440-38-2       | < 5                                                                            | mg/kg                  | 47     | 5     |           | ITA |  |     |
|             |                                                                                   | Barium<br>7440-39-3        | < 5                                                                            | mg/kg                  | 18750  | 5     |           | ITA |  |     |
|             |                                                                                   | Boron<br>7440-42-8         | < 5                                                                            | mg/kg                  | 15000  | 5     |           | ITA |  |     |
|             |                                                                                   | Cadmium<br>7440-43-9       | < 1                                                                            | mg/kg                  | 17     | 1     |           | ITA |  |     |
|             |                                                                                   | Chromium III<br>16065-83-1 | < 5                                                                            | mg/kg                  | 460    | 5     |           | ITA |  |     |
|             |                                                                                   | Chromium VI<br>18540-29-9  | < 0,02                                                                         | mg/kg                  | 0,053  | 0,02  | *         | ITA |  |     |
|             |                                                                                   | Cobalt<br>7440-48-4        | < 5                                                                            | mg/kg                  | 130    | 5     |           | ITA |  |     |
|             |                                                                                   | Copper<br>7440-50-8        | < 5                                                                            | mg/kg                  | 7700   | 5     |           | ITA |  |     |
|             |                                                                                   | Lead<br>7439-92-1          | < 5                                                                            | mg/kg                  | 23     | 5     |           | ITA |  |     |
|             |                                                                                   | Manganese<br>7439-96-5     | 14                                                                             | mg/kg                  | 15000  | 5     |           | ITA |  |     |
|             |                                                                                   | Mercury<br>7439-97-6       | < 5                                                                            | mg/kg                  | 94     | 5     |           | ITA |  |     |
|             |                                                                                   | Nickel<br>7440-02-0        | < 5                                                                            | mg/kg                  | 930    | 5     |           | ITA |  |     |
|             |                                                                                   | Selenium<br>7782-49-2      | < 5                                                                            | mg/kg                  | 460    | 5     |           | ITA |  |     |
|             |                                                                                   | Strontium<br>7440-24-6     | 39                                                                             | mg/kg                  | 56000  | 5     |           | ITA |  |     |
|             |                                                                                   | Tin<br>7440-31-5           | < 3,25                                                                         | mg/kg                  | 180000 | 3,25  |           | ITA |  |     |
|             |                                                                                   | Zinc<br>7440-66-6          | < 5                                                                            | mg/kg                  | 46000  | 5     |           | ITA |  |     |
|             |                                                                                   | Organic Tin                | < 8                                                                            | mg/kg                  | 12     | 8     | #tin<br>* | ITA |  |     |
|             |                                                                                   |                            | 28<br>SAMPLE DESCRIPTION:<br>WHITE PAPER WITH<br>GREY PRINTING<br>(BLACK INK). | Aluminium<br>7429-90-5 | 6      | mg/kg | 28130     | 5   |  | ITA |
|             |                                                                                   |                            |                                                                                | Antimony<br>7440-36-0  | < 5    | mg/kg | 560       | 5   |  | ITA |
|             |                                                                                   |                            |                                                                                | Arsenic<br>7440-38-2   | < 5    | mg/kg | 47        | 5   |  | ITA |
|             |                                                                                   |                            |                                                                                | Barium<br>7440-39-3    | < 5    | mg/kg | 18750     | 5   |  | ITA |



LAB N° 0579 L

Laboratory Manager

Ilenia Francioni

ilenia.francioni@intertek.com

**Intertek Italia S.p.a.**

**Administrative Office** Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)  
**Operational Office** Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)

**Tel. 0039055790873 Fax 0039055791198**

Validated by: Giovanni Servadei

page

25 di 27

| TEST METHOD | SAMPLE DESCRIPTION | PARAMETERS   | RESULT | U.M.  | LIMITS | LQ   | NOTES     | LAB |
|-------------|--------------------|--------------|--------|-------|--------|------|-----------|-----|
|             |                    | Boron        | < 5    | mg/kg | 15000  | 5    |           | ITA |
|             |                    | 7440-42-8    |        |       |        |      |           |     |
|             |                    | Cadmium      | < 1    | mg/kg | 17     | 1    |           | ITA |
|             |                    | 7440-43-9    |        |       |        |      |           |     |
|             |                    | Chromium III | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                    | 16065-83-1   |        |       |        |      |           |     |
|             |                    | Chromium VI  | < 0,02 | mg/kg | 0,053  | 0,02 | *         | ITA |
|             |                    | 18540-29-9   |        |       |        |      |           |     |
|             |                    | Cobalt       | < 5    | mg/kg | 130    | 5    |           | ITA |
|             |                    | 7440-48-4    |        |       |        |      |           |     |
|             |                    | Copper       | < 5    | mg/kg | 7700   | 5    |           | ITA |
|             |                    | 7440-50-8    |        |       |        |      |           |     |
|             |                    | Lead         | < 5    | mg/kg | 23     | 5    |           | ITA |
|             |                    | 7439-92-1    |        |       |        |      |           |     |
|             |                    | Manganese    | 9      | mg/kg | 15000  | 5    |           | ITA |
|             |                    | 7439-96-5    |        |       |        |      |           |     |
|             |                    | Mercury      | < 5    | mg/kg | 94     | 5    |           | ITA |
|             |                    | 7439-97-6    |        |       |        |      |           |     |
|             |                    | Nickel       | < 5    | mg/kg | 930    | 5    |           | ITA |
|             |                    | 7440-02-0    |        |       |        |      |           |     |
|             |                    | Selenium     | < 5    | mg/kg | 460    | 5    |           | ITA |
|             |                    | 7782-49-2    |        |       |        |      |           |     |
|             |                    | Strontium    | 36     | mg/kg | 56000  | 5    |           | ITA |
|             |                    | 7440-24-6    |        |       |        |      |           |     |
|             |                    | Tin          | < 3,25 | mg/kg | 180000 | 3,25 |           | ITA |
|             |                    | 7440-31-5    |        |       |        |      |           |     |
|             |                    | Zinc         | < 5    | mg/kg | 46000  | 5    |           | ITA |
|             |                    | 7440-66-6    |        |       |        |      |           |     |
|             |                    | Organic Tin  | < 8    | mg/kg | 12     | 8    | #tin<br>* | ITA |

**Test performed by:**

ITA: Intertek Italia S.p.a.

Via di Stagno 17 F/G

50055 Lastra a Signa (FI)

Tests marked with star (\*) haven't been Accredia accredited.

**Notes**

#tin = Organotin result is calculated using a 2,44 times factor based on the Tin result.



LAB N° 0579 L

Laboratory Manager

Ilenia Francioni

ilenia.francioni@intertek.com

The partial reproduction of the present Test Report is not allowed without written authorization of the General Manager.  
The content of the present document refers exclusively to the submitted samples and not to the batch that they want to represent.  
A representative portion of the sample is kept for 60 days. Specimen are kept for 30 days.  
Samples are drawn by customer.  
UM: unit of measurement  
Limits are based on Customer's Manual in force available at Intertek Italia S.p.a. - Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)  
Uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence of approximately 95%.  
All the results are reported without considering the uncertainty.  
LQ: Quantification Limit  
As received by the customer, the sample was accepted for testing. The samples description is based only on customer declaration / information

## RESULTS MARKED IN RED EXCEED LIMITS

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

END OF TEST REPORT



LAB N° 0579 L

Intertek Italia S.p.a.  
Administrative Office Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)  
Operational Office Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)  
Tel. 0039055790873 Fax 0039055791198

Laboratory Manager

  
Ilenia Francioni  
[ilenia.francioni@intertek.com](mailto:ilenia.francioni@intertek.com)

Validated by: Giovanni Servadei